

PENTARCH
FORESTRY®

NEW ENGLAND BLACKBUTT

NEW ENGLAND BLACKBUTT

Overview

New England Blackbutt is similar in appearance to Blackbutt but not as durable. The heartwood is described as pale brown with the sapwood being much paler in contrast.

Responsible Wood RW/1-31-217

PEFC PEFC/21-31-217

Sustainably Grown. Australian Made.

Specifications

Botanical Name
Eucalyptus Andrewsii
Origin of Timber
New South Wales
Density Per Standard
Unseasoned: 1150kg/m^3
Seasoned: 850kg/m^3
Hardness
Janka: 9.2
Naturally Lyctid Susceptible
Susceptible
Naturally Termite Resistant
Resistant
Durability Class
In-ground Contact: 2 (Reasonably High)
Outside Above Ground: 2 (Reasonbly High)
Spread-of-Flame Index
6
Smoke-Developed Index
3
Critical Radiant Flux
>2.2 and <4.5
Smoke Development Rate
<750
Fire Group Number
3
Highest BAL Rating
BAL-19
Available Products
Flooring,

Note: Variations within a timber species are normal, therefore photographs, samples and displays can only be indicative of colour and should not be used for final selection. It is normal for natural timber products to react to changes in atmospheric and environmental conditions such as humidity and temperature.

pentarchforestry.com.au
National free call 1800 818 317

©2025 PENTARCH FORESTRY PTY LTD (ABN 22 159 663 420). Pentarch Forestry and the Pentarch Forestry logo are trade marks or registered trade marks of PENTARCH FORESTRY PTY LIMITED or one of its subsidiaries. PEN_0325

PENTARCH FORESTRY®