



PENTARCH  
FORESTRY®

TALLOWWOOD

# TALLOWWOOD

## Overview

**Tallowwood** is predominately yellowish brown with a tinge of olive green with beautiful visible growth rings. This species is very resistant to decay.



## Specifications

### Botanical Name

Eucalyptus Microcorys

### Origin of Timber

New South Wales

### Density Per Standard

Unseasoned: 1200kg/m<sup>3</sup>

Seasoned: 990kg/m<sup>3</sup>

### Hardness

Janka: 8.6

### Naturally Lyctid Susceptible

Susceptible

### Naturally Termite Resistant

Resistant

### Durability Class

In-ground Contact: 1 (High)

Outside Above Ground: 1 (High)

### Spread-of-Flame Index

5

### Smoke-Developed Index

4

### Critical Radiant Flux

>2.2 and <4.5

### Smoke Development Rate

<750

### Fire Group Number

3

### Highest BAL Rating

BAL-19

### Available Products

Cladding, Decking, Flooring, Structural



Responsible Wood

RW/1-31-217



PEFC

PEFC/21-31-217

Sustainably Grown. Australian Made.

Note: Variations within a timber species are normal, therefore photographs, samples and displays can only be indicative of colour and should not be used for final selection. It is normal for natural timber products to react to changes in atmospheric and environmental conditions such as humidity and temperature.

[pentarchforestry.com.au](http://pentarchforestry.com.au)

1800 818 317

©2025 PENTARCH FORESTRY PTY LTD (ABN 22 159 663 420). Pentarch Forestry and the Pentarch Forestry logo are trade marks or registered trade marks of PENTARCH FORESTRY PTY LIMITED or one of its subsidiaries. PEN\_0325



PENTARCH  
FORESTRY®